




8D COG 18g 100mm:




Les Encre 8-dimensional COG threads provide superior tissue repositioning due to the longer length and thickness of each COG. Ideal for use in the face and neck as they possess a unique combination of strength and flexibility. Available 18g-100mm.

Suture USP	Tensile Strength	COG Thickness	COG Length	COG Type	COG Production	Cannula Insertion	Cannula Type
2	57.8 N	.52mm	.87mm		Sliced	1x	Blunt (R)


4D COG 18g 100mm:



Les Encre 4-dimensional COG threads provide ample tissue repositioning. Ideal for use in the face and neck as they possess a unique combination of strength and flexibility. Available in both Polydioxanone (PDO) and Polycaprolactone (PCL), 19-18 Gauge, 60-120mm.

Suture USP	Tensile Strength	COG Thickness	COG Length	COG Type	COG Production	Cannula Insertion	Cannula Type
2	35.6 N	.37mm	.81mm		Sliced	1x	Blunt (R)


Sculpted (Pressure Molded) 18g 100mm:



Les Encre Sculpted threads provide unsurpassed lifting power and tensile strength as the 40 COGs on each thread have been created from a pressure mold rather than from a slice into the suture material. Sculpted threads are ideal for treatment areas that demand the ultimate lift and/or with patients who possess heavy/thick skin. Available in Polydioxanone (PDO), 18g-100mm.

Suture USP	Tensile Strength	COG Thickness	COG Length	COG Type	COG Production	Cannula Insertion	Cannula Type
2	62 N	.25	.2mm	Press COG	Molded	Unlimited	Blunt (W)

EZM (Pressure Molded) 18g 100mm:



Les Encre EZM threads possess the greatest lifting power and tensile strength of any thread in the Les Encre line up. The 49 Fishbone COGs of this thread are intentionally molded close together and uniformly distributed to ensure even the heaviest of tissue is repositioned and stays in place. Fishbone COGs have been found to maintain their shape 12 weeks longer than traditional sliced COGS, thus allowing more time for collagen to form in the newly lifted area. EZM threads are ideal for use in body treatments and/or patients with heavy/thick skin. Available in Polydioxanone (PDO), 19-18 Gauge, 100-120mm.

Suture USP	Tensile Strength	COG Thickness	COG Length	COG Type	COG Production	Cannula Insertion	Cannula Type
2	65 N	1.2	.23mm	Fishbone	Molded	Unlimited	Blunt (W)